

PRODUCT SPECIFICATIONS



CQV Co., Ltd.

Product Name:	CQV PEARL PIGMENT
Trade Name:	Automotive™ Satin Bronze A-620D-SP
Manufacturer:	CQV Co., Ltd. 144, Seongjung-Ro, Jincheon-Eup, Jincheon-Gun, Chungbuk-Do, Korea Tel. 82-43-531-2500, Fax. 82-43-536-0314
Date Prepared:	Rev.2, February 18th, 2013

1. Appearance:	Lustrous Brown, Free-flowing Powder
-----------------------	-------------------------------------

2. Ingredients and Composition					
Ingredients	Composition	By Weight (%)		CAS No.	EINECS
Synthetic Fluorophlogopite	KMg ₃ AlSi ₃ O ₁₀ F ₂	63	- 75	12003-38-2	234-426-5
Iron Oxide	Fe ₂ O ₃	25	- 35	1309-37-1	215-168-2
Silane	-	0	- 2	-	-

3. Particle Size (μm):	Mean Diameters	D10	-	D90	(By Malvern Mastersizer 2000S)
		5	-	25	

4. pH:	3.0 - 6.0	10% Aqueous Suspension
---------------	-----------	------------------------

5. Loss on Drying:	0.5 % max.	ASTM D 280-01
---------------------------	------------	---------------

6. Bulk Density (g/100ml)	37 - 47	ASTM D 716-86
----------------------------------	---------	---------------

7. Density (g/ml)	3.3 - 3.6	ASTM D 153-84
--------------------------	-----------	---------------

8. Oil Absorption (g/100g)	60 - 80	ASTM D 1483-95
-----------------------------------	---------	----------------

9. Conductivity (μ S/cm)	150 max.	10% Aqueous Suspension
---------------------------------	----------	------------------------

10. Trace Elements:	Mercury (Hg)	0.005 % max.	USEPA 3052
	Arsenic (As)	0.005 % max.	
	Lead (Pb)	0.010 % max.	
	Cadmium (Cd)	0.010 % max.	
	Hexavalent Chromium (Cr ⁶⁺)	0.001 % max.	USEPA 3060A