

PRODUCT SPECIFICATIONS



CQV Co., Ltd.

Product Name:	CQV PEARL PIGMENT
Trade Name:	Automotive™ Fine Gold A-701D-SP
Manufacturer:	CQV Co., Ltd. 144, Seongjung-Ro, Jincheon-Eup, Jincheon-Gun, Chungbuk-Do, Korea Tel. 82-43-531-2500, Fax. 82-43-536-0314
Date Prepared:	Rev.2, February 18th, 2013

1. Appearance:	Fine Silk White, Free-flowing Powder
-----------------------	--------------------------------------

2. Ingredients and Composition					
Ingredients	Composition	By Weight (%)		CAS No.	EINECS
Synthetic Fluorophlogopite	$KMg_3AlSi_3O_{10}F_2$	41	- 54	12003-38-2	234-426-5
Tin Oxide	SnO_2	0	- 1	18282-10-5	242-159-0
Titanium Dioxide (Rutile)	TiO_2	46	- 56	1317-80-2	215-282-2
Silane	-	0	- 2	-	-

3. Particle Size (μm):	Mean Diameters	D10	-	D90	By Malvern Mastersizer 2000S
		5	-	25	

4. pH:	3.0 - 6.0	10% Aqueous Suspension
---------------	-----------	------------------------

5. Loss on Drying:	0.5 % max.	ASTM D 280-01
---------------------------	------------	---------------

6. Bulk Density (g/100ml)	51 - 61	ASTM D 716-86
----------------------------------	---------	---------------

7. Density (g/ml)	3.2 - 3.5	ASTM D 153-84
--------------------------	-----------	---------------

8. Oil Absorption (g/100g)	55 - 75	ASTM D 1483-95
-----------------------------------	---------	----------------

9. Conductivity ($\mu S/cm$)	150 max.	10% Aqueous Suspension
--	----------	------------------------

10. Trace Elements:	Mercury (Hg)	0.005 % max.	USEPA 3052
	Arsenic (As)	0.005 % max.	
	Lead (Pb)	0.010 % max.	
	Cadmium (Cd)	0.010 % max.	
	Hexavalent Chromium (Cr^{6+})	0.001 % max.	USEPA 3060A