

**PRODUCT SPECIFICATIONS****CQV Co., Ltd.**

<b>Product Name:</b>	<b>CQV PEARL PIGMENT</b>
<b>Trade Name:</b>	<b>Reflex™ Silk White N-801F</b>
<b>Manufacturer:</b>	<b>CQV Co., Ltd.</b> 144, Seongjung-Ro, Jincheon-Eup, Jincheon-Gun, Chungbuk-Do, Korea Tel. 82-43-531-2500, Fax. 82-43-536-0314
<b>Date Prepared:</b>	Rev. 3, February 18th, 2013

<b>1. Appearance:</b>	Fine Silk White, Free-flowing Powder
-----------------------	--------------------------------------

**2. Ingredients and Composition**

Ingredients	Composition	By Weight (%)			CAS No.	CI No.
Mica	$K_2O \cdot 3Al_2O_3 \cdot 6SiO_2 \cdot 2H_2O$	43	-	54	12001-26-2	77019
Tin Oxide	$SnO_2$	0	-	1	18282-10-5	77861
Titanium Dioxide	$TiO_2$	46	-	56	13463-67-7	77891

<b>3. Particle Size (<math>\mu m</math>):</b>	Mean Diameters	D10	-	D90	(By Malvern Mastersizer 2000S)
		2	-	12	

<b>4. pH:</b>	7.0 - 11.0	(10% Aqueous Suspension)
---------------	------------	--------------------------

<b>5. Loss on Drying:</b>	0.5 % max.
---------------------------	------------

<b>6. Loss on Ignition:</b>	0.5 % max.
-----------------------------	------------

<b>7. Density (<math>g/cm^3</math>)</b>	2.8 - 3.2
---	-----------

<b>8. Oil Absorption (g/100g)</b>	65 - 85
-----------------------------------	---------

<b>9. Acid Soluble Substances:</b>	2.0 % max.
------------------------------------	------------

<b>10. Trace Elements:</b>	Mercury (Hg)	1 ppm max.	IEC 62321
	Lead (Pb)	10 ppm max.	
	Cadmium (Cd)	1 ppm max.	
	Hexavalent Chromium( $Cr^{6+}$ )	5 ppm max.	