

**PRODUCT SPECIFICATIONS****CQV Co., Ltd.**

<b>Product Name:</b>	<b>CQV PEARL PIGMENT</b>
<b>Trade Name:</b>	<b>Reflex™ Satin Russet R-660D</b>
<b>Manufacturer:</b>	<b>CQV Co., Ltd.</b> 144, Seongjung-Ro, Jincheon-Eup, Jincheon-Gun, Chungbuk-Do, Korea Tel. 82-43-531-2500, Fax. 82-43-536-0314
<b>Date Prepared:</b>	Rev. 2, February 18th, 2013

<b>1. Appearance:</b>	Lustrous Reddish, Free-flowing Powder
-----------------------	---------------------------------------

**2. Ingredients and Composition**

Ingredients	Composition	By Weight (%)	CAS No.	EINECS
Synthetic Fluorophlogopite	$\text{KMg}_3\text{AlSi}_3\text{O}_{10}\text{F}_2$	45 - 55	12003-38-2	234-426-5
Iron Oxide	$\text{Fe}_2\text{O}_3$	45 - 55	1309-37-1	215-168-2

<b>3. Particle Size (<math>\mu\text{m}</math>):</b>	Mean Diameters	D10	-	D90	(By Malvern Mastersizer 2000S)
		5	-	25	

<b>4. pH:</b>	7.0 - 11.0	(10% Aqueous Suspension)
---------------	------------	--------------------------

<b>5. Loss on Drying:</b>	0.5 % max.
---------------------------	------------

<b>6. Loss on Ignition:</b>	0.5 % max.
-----------------------------	------------

<b>7. Density (<math>\text{g}/\text{cm}_3</math>)</b>	3.6 - 3.8
---	-----------

<b>8. Oil Absorption (<math>\text{g}/100\text{g}</math>)</b>	40 - 60
--	---------

<b>9. Acid Soluble Substances:</b>	2.0 % max.
------------------------------------	------------

<b>10. Trace Elements:</b>	Mercury (Hg)	1 ppm max.	IEC 62321
	Lead (Pb)	10 ppm max.	
	Cadmium (Cd)	5 ppm max.	
	Hexavalent Chromium( $\text{Cr}^{6+}$ )	5 ppm max.	